



TYPE APPROVAL CERTIFICATE

Certificate no.:
TAE0000039
Revision No:
5

This is to certify:

that the **Electric Power Cable**

with type designation(s)
M2XH, M2XCH, M2XCH EMC

issued to

Untel Kablolari San. ve Tic. A.S.
Dilovası, Türkiye

is found to comply with

DNV rules for classification – Ships, offshore units, and high speed and light craft

Application:

General power and lighting.

Products approved by this certificate are accepted for installation on all vessels classed by DNV.

| Type | Rated voltage (kV) | Temp. class (°C) |
|------------------|--------------------|------------------|
| M2XH | 0,6/1 | 90 |
| M2XCH | 0,6/1 | 90 |
| M2XCH EMC | 0,6/1 | 90 |

Issued at **Høvik** on **2024-08-15**

for **DNV**

This Certificate is valid until **2029-06-22**.

DNV local unit: **Istanbul**

Approval Engineer: **Ivar Bull**

This Certificate is subject to terms and conditions overleaf. Any significant change in design or construction may render this Certificate invalid. The validity date relates to the Type Approval Certificate and not to the approval of equipment/systems installed.

LEGAL DISCLAIMER: Unless otherwise stated in the applicable contract with the holder of this document, or following from mandatory law, the liability of DNV AS, its parent companies and their subsidiaries as well as their officers, directors and employees ("DNV") arising from or in connection with the services rendered for the purpose of the issuance of this document or reliance thereon, whether in contract or in tort (including negligence), shall be limited to direct losses and under any circumstance be limited to 300,000 USD.



Product description

Type: **M2XH, M2XCH, M2XCH EMC 0,6/1 kV**
 Conductors: Plain or tinned stranded copper (class 2 or class 5)
 Core insulation: Cross-Linked PolyEthylene (XLPE)

Option: Bedding/inner covering/filler

Bedding/Inner covering: Halogen free & flame retardant compound
 Filler: Flame retardant & non hygroscopic material

Braid: Plain or tinned Copper wires (C Type)
 EMC Screen: Electrolytic copper tape (EMC Type)
 Outer sheath: Halogen Free Compound SHF1 or SHF2

| No of cores: | Cross sectional area [mm ²] |
|------------------------------------|---|
| 1 | 1 - 300 |
| 2 | 1 – 35 |
| 3 | 1 - 185 |
| 4 | 1 - 120 |
| 5 | 1 - 16 |
| 7 | 1 1,5 2,5 |
| 10, 12, 14, 16, 19, 24, 27, 37, 60 | 1,5 |

Application/Limitation

The requirements of SOLAS Amendments Chapter II-1, Part D, Reg, 45, 5,2 (provision to be taken to limit Fire Propagation along Bunches of Cables or Wires) are fulfilled without any additional measures,

Type Approval documentation

Data sheets:

FR 70-022 Rev. 0 Rev. Tar. 01.09.2009.
 FR 70-023 Rev. 0 Rev. Tar. 01.09.2009.
 FR 70-024 Rev. 0 Rev. Tar. 01.09.2009.

Test reports: Üntel test reports dated 11/10/2010

Tests carried out

| Standard | Release | General description | Limitation |
|----------------|---------|---|---|
| DNV CP-0399 | 2021-08 | Electric cables. | |
| IEC 60092-350 | 2020-01 | Electrical installations in ships - Part 350: General construction and test methods of power, control and instrumentation cables for shipboard and offshore applications | |
| IEC 60092-360 | 2021-01 | Electrical installations in ships - Part 360: Insulating and sheathing materials for shipboard and offshore units, power, control, instrumentation and telecommunication cables | |
| IEC 60092-353 | 2024-06 | Electrical installations in ships - Part 353: Power cables for rated voltages 1 kV and 3 kV | |
| IEC 60332-3-22 | 2018-07 | Tests on electric and optical fibre cables under fire conditions - Part 3-22: Test for vertical flame spread of vertically mounted bunched wires or cables - Category A | Charred portion of sample does not exceed 2,5m above bottom edge of burner. |
| IEC 60754-1 | 2019-11 | Test on gases evolved during combustion of materials from cables - Part 1: Determination of the halogen acid gas content | Low Halogen: <0,5% Halogen |
| IEC 60754-2 | 2019-11 | Test on gases evolved during combustion of materials from cables - Part 2: Determination of acidity (by pH measurement) and conductivity | Halogen free: pH > 4,3 Conductivity < 10µS/mm |

| Standard | Release | General description | Limitation |
|---------------|---------|--|---------------------------------------|
| IEC 61034-1/2 | 2019-11 | Measurement of smoke density of cables burning under defined conditions – Part 1: Test apparatus Part 2: Test procedure and requirements | Low smoke Light transmittance >60% |

Marking of product

ÜNTEL – M2XH or M2XCH or M2XCH EMC – size – IEC 60332 – Cat. A – 0,6/1 kV – Lot nr.

Periodical assessment

The scope of the periodical assessment is to verify that the conditions stipulated for the Type approval are complied with and that no alterations are made to the product design or choice of materials.

The main elements of the assessment are:

- Inspection on factory samples, selected at random from the production line (where practicable)
- Results from Routine tests (RT) and selected type tests (ref. to applicable class programs) checked (if not available these tests shall be carried out)
- Review of type approval documentation
- Review of possible change in design, materials and performance
- Ensuring traceability between manufacturer's product type marking and Type Approval Certificate.

Periodical assessment is to be performed after 2 years and after 3.5 years. A renewal assessment will be performed at renewal of the certificate.

END OF CERTIFICATE